

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 903 178 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
26.11.2003 Bulletin 2003/48

(51) Int Cl.7: **B01J 29/40, C10G 11/05**

(21) Application number: **98307583.9**

(22) Date of filing: **17.09.1998**

(54) **A pentasil-type molecular sieve containing composition, its preparation method and use**

Zusammensetzung, die Molekularsieve vom Pentasil-Typ enthält, sowie ihre Herstellung und Verwendung

Composition contenant un tamis moléculaire de type pentasil, son procédé de préparation et son utilisation

(84) Designated Contracting States:
DE FI FR GB NL

(30) Priority: **17.09.1997 CN 97116445**
17.09.1997 CN 97116435

(43) Date of publication of application:
24.03.1999 Bulletin 1999/12

(73) Proprietors:
• **China Petro-Chemical Corporation**
Beijing (CN)
• **RESEARCH INSTITUTE OF PETROLEUM**
PROCESSING, SINOPEC
Beijing (CN)

(72) Inventors:
• **Zhang, Fengmei, Res. Inst. Petroleum**
Proc.SINOPEC
Haidian District, Beijing (CN)
• **Shu, Xingtian, Res. Inst. Petroleum Proc.**
SINOPEC
Haidian District, Beijing (CN)
• **Shi, Zhicheng, Res. Inst. Petroleum Proc.**
SINOPEC
Haidian District, Beijing (CN)
• **Wang, Weldong, Res. Inst. Petroleum Proc.**
SINOPEC
Haidian District, Beijing (CN)
• **Qin, Fengming, Res. Inst. Petroleum Proc.**
SINOPEC
Haidian District, Beijing (CN)

• **Wang, Xieqing, Res. Inst. Petroleum Proc.**
SINOPEC
Haidian District, Beijing (CN)

(74) Representative: **Colmer, Stephen Gary et al**
Mathys & Squire
100 Gray's Inn Road
London WC1X 8AL (GB)

(56) References cited:
EP-A- 0 030 811 EP-A- 0 040 463
EP-A- 0 068 755 EP-A- 0 393 667
US-A- 3 702 886 US-A- 4 137 195
US-A- 4 581 215

• **DATABASE WPI Section Ch, Week 9427 Derwent**
Publications Ltd., London, GB; Class E17, AN
94-221804 XP002088540 & JP 06 157359 A
(COSMO SOGO KENKYUSHO KK), 3 June 1994
• **DATABASE WPI Section Ch, Week 8943 Derwent**
Publications Ltd., London, GB; Class A41, AN
89-312268 XP002088526 & JP 01 228921 A
(NIPPON PETROCHEMICALS CO LTD), 12
September 1989
• **DATABASE COMPENDEX ENGINEERING**
INFORMATION, INC., NEW YORK, NY, US CHEN
LIANZHANG ET AL: "MODIFIED ZSM-5
CATALYSTS FOR INCREASING P-XYLENE
SELECTIVITY IN TOLUENE
DISPROPORTIONATION REACTION"
XP002088525 & SHIYOU XUEBAO SHIYOU
HUAGONG JUN 1987, vol. 3, no. 2, June 1987,
pages 38-44,

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 903 178 B1

Description

[0001] This invention relates to a pentasil-type molecular sieve containing composition which can be applied in catalytic cracking reaction for producing more ethylene and propylene, and its preparation method.

[0002] The pentasil-type molecular sieves invented by Mobil Corporation, such as ZSM-5 (USP3,702,886; 1976), ZSM-8 (GB1334243A), ZSM-11 (USP3,709,979; 1973) and ZSM-5/ZSM-11 (USP4,289,607; 1981), after modification, are widely used in hydrocarbon conversion reactions such as aromatic hydrocarbon alkylation, disproportionation, isomerization, catalytic cracking, catalytic dewaxing and synthesis of gasoline from methanol etc., in which ZSM-5 is most successfully used.

[0003] ZSM-5 molecular sieves was synthesized formerly by using organic amines as templates, including tetrapropylammonium, tetraethylammonium, hexamethylenediamine, ethylenediamine, n-butylamine and ethylamine etc.. Because of the expensive cost and environmental contamination, the method of synthesizing ZSM-5 without using organic substances has been widely explored at the same time. For example, in EP111748A (1984), ZSM-5 zeolite is synthesized by using water glass, aluminum phosphate and phosphoric acid; in CN85100463A, ZSM-5 zeolite is synthesized by using water glass, inorganic aluminum salts and mineral acid as initial materials; in CN1058382A, rare-earth containing ZSM-5 zeolite is synthesized by using water glass, aluminium phosphate and mineral acids as source materials and REY or REHY as crystal seeds. JP8571519 and JP8577123 reported a method in which ZSM-5 molecular sieve is synthesized by adding ZSM-5 as crystal seeds under the condition that no amine is used.

[0004] In order to satisfy the different kinds of requirements in different reactions, a lot of methods of modifying ZSM-5 molecular sieve and their different effects are reported. For example, methods for modifying ZSM-5 molecular sieve using a phosphorus-containing compound are reported in USP3,972,382 and USP3,965,208, in which HZSM-5 with a $\text{SiO}_2/\text{Al}_2\text{O}_3$ ratio of 70 is reacted with trimethyl phosphite to prepare a phosphorus containing molecular sieve. This preparation method has several disadvantages of complicated conditions as well as high costs, and the samples obtained have lower reactivity than the samples not containing phosphorus, but have an advantage of high selectivity.

[0005] USP4,365,104, USP4,137,195, USP4,128,592 and USP4,086,287 report a method of modifying ZSM-5 molecular sieve using P and Mg for the purpose of improving the para-xylene selectivity by using the modified molecular sieve in xylene isomerization, toluene alkylation with methanol and toluene disproportionation reactions. The introduction of P and Mg is for increasing the molecular sieve's shape selectivity. On the other hand, the molecular sieve's acidity and reactivity in hydrocarbon conversion reaction are decreased by the modification. In these patents, P and Mg are impregnated in two steps separately. That is the molecular sieve or molecular sieve containing catalyst is firstly impregnated with $\text{NH}_4\text{H}_2\text{PO}_4$ or $(\text{NH}_4)_2\text{HPO}_4$ aqueous solution, and then filtered, dried, and calcined; and secondly impregnated with $\text{Mg}(\text{NO}_3)_2$ or $\text{Mg}(\text{CH}_3\text{COO})_2$ aqueous solution, then filtered, dried and calcined, then the P and Mg modified molecular sieve or catalyst containing the molecular sieve is obtained. In this method, the content of P and Mg has an uncertainty, since it depends on reaction condition of temperature, time and calcination. At the same time, the Mg can not be well dispersed. According to USP4,137,195, in addition to the H-form, other forms of zeolite wherein the original alkali metal has been replaced by ion exchange with other suitable ions of groups IB to VIII may be used.

[0006] In USP4,260,843, a method of modifying ZSM-5 molecular sieve with P and Be for increasing the shape selectivity is reported. USP4,288,647 has described a method of modifying ZSM-5 molecular sieves with Ca, Sr, Ba and P for improving the shape selectivity. In these patents, the method for modifying the molecular sieve is basically the same as the above-mentioned method with P and Mg, but the activity of the modified molecular sieve is even further lowered.

[0007] In above patents, the precursor of the molecular sieve is described as that its $\text{SiO}_2/\text{Al}_2\text{O}_3$ ratio is higher than 12, generally higher than 30 (USP3,972,832). The content of modification P element is generally higher than 0.25%wt, the content of alkaline earth element is required to be higher than 0.25%wt, and in the range of 0.25~25%wt. In the examples of embodiment, the content of alkaline-earth element (Mg, Ca etc.) is generally higher than the content of P element. The object of the above patents is mainly to increase the shape selectivity of the molecular sieves, which are all used in isomerization and disproportionation reactions for booming the selectivity to xylene. Generally, it is acknowledged that after alkaline earth modification, the molecular sieve's acidity is decreased, and its catalytic activity in hydrocarbon conversion is decreased too.

[0008] Catalytic pyrolysis process for producing ethylene is a new way to increase ethylene production. Conventional steam cracking method for producing ethylene has the disadvantages of high cracking temperature and strict requirement for the quality of the feedstock. People hold that the production of ethylene by steam cracking method is carried out through the mechanism of free radical reaction, so it requires high reaction temperature. The applicant of this invention has set forth a series of processes and catalysts in catalytic cracking for producing lower carbon olefins in the patents such as USP4,980,053, USP5,326,465, USP5,358,918, USP5,380,690, USP5,670,037, etc. In all these patents, cracking catalysts generally contain higher silica pentasil-type zeolites having P and rare-earth elements, and are all for increasing $\text{C}_3\sim\text{C}_5$ olefins production, with relatively lower ethylene yield. Under the condition of catalytic cracking with catalyst containing ZSM-5 molecular sieve, the $\text{C}_3\sim\text{C}_5$ olefins are remarkably increased because of

the medium sized pore system and higher shape selective capability, however, the reaction is still through carbonium ion mechanism. In CN1083092A, a catalytic pyrolysis process for producing ethylene and propylene is reported by using cross-linked pillared clay-containing molecular sieve or rare-earth containing pentasil-type molecular sieve as catalyst at a temperature range of 680~780°C in which ethylene can remarkably be increased. The catalyst does not contain metallic component.

[0009] Considering that producing more ethylene needs higher reaction and regeneration temperatures, it requires that the molecular sieve active components must have better thermal and hydrothermal stability in respect of both the structure and active center, that is under the severe hydrothermal treatment condition, the molecular sieve must maintain its high activity. In addition, it is needed to increase the formation of carbonium ion and its direct cracking, especially increasing the formation of primary carbonium ion and its direct cracking, at the same time, depressing the isomerization of primary carbonium ion to secondary or tertiary carbonium ion. Therefore, the shape selective cracking capability of the molecular sieve is required to be strengthened, while desirably it should have certain dehydrogenation capability for increasing olefin yield.

[0010] The object of this invention is to provide a pentasil-type molecular sieve containing composition which can be applied in catalytic cracking reaction for producing more ethylene and propylene, and which has better thermal and hydrothermal stability, and can increase the ethylene yield further when being used in catalytic pyrolysis process, in comparison with the catalytic materials of the prior art.

[0011] Another object of this invention is to provide a method for preparing said pentasil-type molecular sieve containing composition.

[0012] The pentasil-type molecular sieve containing composition of this invention comprises essentially 85~98%wt, preferably 88~95%wt, of pentasil-type molecular sieve having a $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio of 15~60, 1~10%wt, preferably 2~8%wt, of phosphorus (based on P_2O_5), 0.3~5% wt, preferably 0.5~3%wt of Mg or Ca (based on oxide), and 0.3~5%wt, preferably 0.5~3%wt, of a metal selected from Ni, Cu or Zn (based on oxide).

[0013] According this invention, the said pentasil-type molecular sieve in said composition is ZSM-5, ZSM-8 or ZSM-11 structure type molecular sieve, in which the preferred molecular sieve is ZSM-5 structure type, with a silica to alumina molar ratio of 15~60, preferably 15~40, and lower silica to Alumina ratio is beneficial for yielding more ethylene.

[0014] The said alkaline earth metal in said composition of this invention is selected from magnesium or calcium.

[0015] The said transition metal in said composition of this invention is a metal which has dehydrogenation function, selected from Ni, Cu or Zn.

[0016] In the composition of this invention, the said phosphorus, Ca or Mg and a metal selected from Ni, Cu or Zn are introduced into said molecular sieve by impregnating or mixing molecular sieve with their compounds. Then the molecular sieve is dried and calcined to cause interaction. Thereby the phosphorus, Ca or Mg and a metal selected from Ni, Cu or Zn are solidly fixed onto the molecular sieve.

[0017] According this invention, the preparation method of said pentasil-type zeolite containing composition of the invention comprises firstly adding a pentasil-type molecular sieve to an aqueous solution which contains phosphorus-containing compound, Mg or Ca compound and a compound of Ni, Cu or Zn, mixing thoroughly and impregnating for above 0.5 hour, the obtained mixture contains (in dry basis) 85~98%wt, preferably 88~95%wt of pentasil-type zeolite, 1~10%wt, preferably 2~8%wt, of phosphorus (based on P_2O_5), and 0.3~5%wt, preferably 0.5~3%wt, of Mg or Cu (based on oxide), and 0.3~5%wt, preferably 0.5~3%wt, of a metal selected from Cu, Ni or Zu (based on oxide), the mixture is then dried, and calcined at 450 to 650°C for 1~4 hours.

[0018] In the method of this invention, the said phosphorus containing compound may be phosphoric acid, hydrogen phosphate, dihydric phosphate or phosphate, in which phosphoric acid is preferable.

[0019] In the method of this invention, the said alkaline earth metal compound is the compound of magnesium or calcium, which can be their nitrate, sulfate or chloride, preferably nitrate or chloride.

[0020] In the method of this invention, the compound of Ni, Cu or Zn can be their nitrate, sulfate or chloride, preferably their nitrate or chloride, most preferably their chloride.

[0021] In the method of this invention, the said mixture has a water to solid weight ratio of (1~3):1.

[0022] In the method of this invention, the said calcination can be proceeded in air or in steam.

[0023] In comparison with the method of prior art (stepwise impregnation and calcination in USP4,137,195), the method of this invention only needs one-step-through impregnation and calcination, it does not need series of steps for impregnation and calcination. So this method has not only simplified the preparation process, but also reduced the energy consumption and preparation cost; moreover, the product obtained has adequate hydrothermal stability, and when used in catalytic pyrolysis cracking, its ethylene yield is higher than that of the method of prior art.

[0024] In the reports of earlier patents, the introduction of activation element such as alkaline earth metal or transition metal can enhance the shape selective property, but the reaction activity is decreased. This is because the amount of activation element introduced is restrained by the zeolite. In the course of research for this invention, it is found that the amount of activation element introduced is correlated with the silica to alumina ratio of the zeolite. That is, the lower is the silica to alumina ratio, the higher is the capacity of activation elements to be introduced. For molecular sieve

having a lower silica to alumina ratio, when a larger amount of activation elements is introduced, it can still maintain high reaction activity. In view of that the higher the amount of activation element is introduced, the stronger its shape selective property will be, hence, selecting a zeolite with lower silica to alumina ratio is beneficial for producing ethylene in catalytic pyrolysis cracking reaction. However, in the prior art, it is generally emphasized that higher silica to alumina ratio is of benefit to the reaction. This is a special feature of this invention.

[0025] In this invention, it is found that, after the activation element, such as alkaline earth metal, is introduced, the number of Bronsted acid sites of the zeolite can be reduced, while the Lewis acid sites is relatively increased. The increase of Lewis acid sites is beneficial for ethylene production.

[0026] The transition metals such as Ni, Co, Zn, Cu, Cr, Mn introduced into pentasil-type molecular sieve are generally used as an active component for hydrogenation or dehydrogenation or aromatization reactions. This is because these elements have stronger hydrogen transfer property. In the catalytic cracking reaction for producing ethylene, the introduction of these elements can enhance the hydrogen transfer ability of the molecular sieve but is not of benefit to increasing the selectivity to olefin products. In our research work, it is found that the hydrogen transfer capability of transition metal is apparently suppressed in the presence of phosphorus element, and the selectivity to olefin, especially to ethylene and propylene, are increased, because of its dehydrogenation activity. In this invention, therefore, on the basis of the introduction of phosphorus and alkaline earth elements into the pentasil-type zeolite, the transition metals Ni, Zn, Cu are further introduced for improving the ethylene yield. At the same time, the presence of phosphorus can enhance the hydrothermal stability of the molecular sieve. This is another distinct feature of this invention.

[0027] In conclusion, this invention has provided a molecular sieve containing composition, by which the lower carbon olefins especially ethylene and propylene produced by catalytic pyrolysis cracking reaction can be remarkably increased in comparison with the prior art. In addition, the said composition has good hydrothermal stability.

[0028] The ZSM-5 molecular sieve obtained by synthesis belongs to orthorhombic crystal system. By inorganic ammonium exchange, $\text{NH}_4\text{ZSM-5}$ can be prepared therefrom, and the HZSM-5 is obtained after calcination at $500\sim 600^\circ\text{C}$. In these preparation processes, the structural symmetry of the molecular sieve is found fundamentally to be unchanged. Under severe high temperature hydrothermal treatment, change in the structure symmetry of the ZSM-5 molecular sieve will occur, in which, its critical feature is that the peak at $2\theta = 24.4^\circ$ in x-ray diffraction (XRD) pattern becomes widened or even split. This change in structural symmetry is coincidental with the decrease of reaction activity of the molecular sieve in cracking reaction. So, in the examples of this invention and the comparative examples, the hydrothermal stability of active centers can be judged by x-ray diffraction (XRD) pattern. At the same time, the activity is evaluated with pulse-micro-reaction using tetradecane (nC_{14}) as reactant.

[0029] In this invention, the molecular sieve materials used in the examples and comparative examples and their properties are listed as follows:

1. ZSM-5A, produced by the Zhoucun Catalyst Plant of the Qilu Petrochemical Co., synthesized with ethylamine as organic template, demtemplated by calcination. Its silica to alumina molar ratio is 52.0, Na_2O content is 0.10%wt after NH_4^+ exchange.

2. ZSM-5B, produced by the catalyst plant of Changling Refinery, with a silica to alumina molar ratio of 25.0 and a Na_2O content of 0.10%wt after NH_4^+ exchange.

3. ZSM-5C, synthesized in our laboratory, with a silica to alumina ratio of 19.0, and a Na_2O content of 0.05%wt after NH_4^+ exchange.

[0030] In this invention, the chemical compositions of molecular sieves used in the examples and comparative examples are determined by x-ray fluorescence (XRF) spectrometry.

[0031] Further explanation is made by the examples as follows in this invention.

SYNTHESIS of ZSM-5C:

[0032] This example illustrates the synthesis of the ZSM-5 zeolite having a lower silica to alumina ratio used in this invention.

[0033] 24.6g of sodium meta-aluminate was dissolved in 667g of decaionized water, then 71.7g of H_3PO_4 (85wt%) was added with stirring. After homogeneously stirring, the solution was added into 643g of water glass (SiO_2 28wt%, Na_2O 9.0wt%) and stirred for 4 hours, then 19.5g of ZSM-5 molecular sieve (produced by Zhoucun catalyst plant, $\text{SiO}_2/\text{Al}_2\text{O}_3=52.0$) was added as crystal seeds. After continuously stirring for 2 hours, the mixture was transferred to a stainless steel autoclave, crystallized under stirring at 175°C for 15 hours and then cooled to room temperature. The crystallized product was then filtered out, washed and dried at 120°C , and the ZSM-5C sample was obtained. The relative crystallinity of the sample (compared to ZSM-5A) was 92% given by XRD analysis.

[0034] This sample was exchanged under a 1:1:20 weight ratio of molecular sieve to ammonium nitrate to decaionized water at 90°C for 2 hours, then filtered and water washed, the filter cake was exchanged again under the same

conditions, and dried at 120°C. The ammonium-type ZSM-5C sample was obtained with a Na₂O content of 0.05%wt.

COMPARATIVE EXAMPLE 1:

- 5 [0035] This comparative example illustrates the effect of ordinary HZSM-5 molecular sieves.
- [0036] A moderate amount of NH₄⁺ exchanged ZSM-5A molecular sieve was taken for calcination in ceramic vessel, then calcined in muffle furnace at 550°C for 2 hours. The obtained sample was pelletized to 20~40 mesh particles. A moderate amount of the particle molecular sieve was fed into stainless steel tube reactor, then aged at 100% steam atmosphere for 4 hours at a temperature of 800°C with decationized water at a space velocity of 8h⁻¹. Under the same
- 10 hydrothermal treatment conditions, the ammonium exchanged molecular sieve samples of ZSM-5B and 5C were calcined and high temperature hydrothermal treated. The obtained samples were designated respectively as DZSM-5A, DZSM-5B and DZSM-5C. X-ray diffraction analysis and tetradecane (nC₁₄) micro-pulse reactor evaluation were performed for the above three aged samples and the results are listed in table 1. The conditions of micro-pulse reactor evaluation were that the amount of molecular sieve loaded was 0.1g, reaction temperature was 480°C and N₂ flow rate was 30ml/min, the pulse feeding of nC₁₄ was 0.5 micro-liter.
- 15

TABLE 1

Zeolite	XRD 24.4 ° Peak	conversion of nC ₁₄ , %
DZSM-5A	double peaks	26.6
DZSM-5B	double peaks	33.1
DZSM-5C	double peaks	30.5

- 20
- 25 [0037] It can be observed that after high temperature steam treatment, the structure of ordinary HZSM-5 molecular sieves has changed, since the 2θ=24.4° peaks have split into double peaks, and the conversion of nC₁₄ has been lowered remarkably at the same time.

COMPARATIVE EXAMPLE 2:

- 30 [0038] This comparative example illustrates the effects of the ZSM-5 modified by P and Mg elements of the prior art.
- [0039] 19g ZSM-5B molecular sieve sample (dry basis) was put into an aqueous solution prepared by dissolving 1.9g (NH₄)₂HPO₄ in 40g decationized water. After stirring at room temperature for 12 hours, it was dried at 120°C and calcined at 550°C for 2 hours. The obtained sample was again mixed with another aqueous solution prepared by
- 35 dissolving 1.51g Mg(CH₃COO)₂ · 4H₂O in 40g decationized water. After stirring at room temperature for 12 hours, it was then dried at 120°C and calcined at 550°C for 2 hours. This sample is denoted as D-2. XRF analysis showed that the contents of P₂O₅ and MgO were 5.0%wt and 1.4%wt respectively.
- [0040] According to the method described in comparative example 1, the sample D-2 was pelletized, hydrothermally aged at 800°C for 4 hours in 100% steam atmosphere. The results of XRD and nC₁₄ pulse-micro-reactor evaluation are listed in table 2.
- 40

COMPARATIVE EXAMPLE 3:

- 45 [0041] 19g ZSM-5A molecular sieve sample (dry basis) was added to an aqueous solution prepared by dissolving 1.9g (NH₄)₂HPO₄ in 40g decationized water, the mixture was stirred at room temperature for about 12 hours, then dried at 120°C, and calcined at 550°C for 2 hours.
- [0042] The obtained sample was further mixed with an aqueous solution prepared by dissolving 0.43g ZnCl₂ in 40g decationized water. The mixture was stirred at room temperature for 12 hours, then dried at 120°C and calcined at 550°C for 2 hours. The obtained molecular sieve is denoted as D-3. XRF analysis showed that the contents of P₂O₅ and ZnO were 5.0%wt and 1.3%wt respectively.
- 50 [0043] According to the method described in comparative example 1, the above sample D-3 is pelletized and hydrothermally aged at 840°C for 4 hours in 100% steam atmosphere. The results of XRD and nC₁₄ micro-pulsereactor evaluation are listed in table 2.

EXAMPLE 1:

- 55 [0044] 19g ZSM-5B molecular sieve sample (dry basis) was added into an aqueous solution prepared by mixing 1.62g 85%wt H₃PO₄, 40g decationized water, 1.48g MgCl₂ · 6H₂O and 0.70g Ni(NO₃)₂ · 6H₂O. The mixture is stirred

at room temperature for 2 hours, then dried at 120°C, and calcined at 550°C for 2 hours. The obtained molecular sieve is denoted as ZEP-11. According to XRF analysis, the content of P_2O_5 , MgO and NiO were 4.9%, 1.4% and 0.86%wt respectively.

[0045] According to the method described in comparative example 1, the ZEP-11 sample was aged under high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reactor evaluation are given in table 2.

EXAMPLE 2:

[0046] 19g ZSM-5B molecular sieve sample (dry basis) was added into an aqueous solution prepared by mixing 1.62g 85%wt H_3PO_4 , 40g decationized water, 0.98g $MgCl_2 \cdot 6H_2O$ and 2.09g $Ni(NO_3)_2 \cdot 6H_2O$. The mixture was stirred at room temperature for 2 hours, then dried at 120°C, and calcined at 550°C for 2 hours. The obtained molecular sieve sample was denoted as ZEP-12. XRF analysis showed that the contents of P_2O_5 , MgO and NiO were 4.9%, 0.91% and 2.6% by weight respectively.

[0047] According to the method described in comparative example 1, the obtained ZEP-12 sample was aged under high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reactor evaluation are listed in table 2.

EXAMPLE 3:

[0048] 19g ZSM-5B molecular sieve sample (dry basis) was added in an aqueous solution prepared by dissolving 1.62g 85%wt H_3PO_4 , 1.48g $MgCl_2 \cdot 6H_2O$ and 0.33g $ZnCl_2$ in 40g decationized water. The mixture was stirred at room temperature for 2 hours, then dried at 120°C, and calcined at 550°C for 2 hours. The obtained molecular sieve was denoted as ZEP-13. XRF analysis showed that, the contents of P_2O_5 , MgO and ZnO were 4.9%, 1.4% and 0.94% by weight respectively.

[0049] According to the method described in comparative example 1, the obtained ZEP-13 sample was aged under high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reaction evaluation are listed in table 2.

EXAMPLE 4:

[0050] 19g ZSM-5C molecular sieve sample (dry basis) was added in an aqueous solution prepared by mixing 1.62g 85%wt H_3PO_4 , 40g decationized water, 1.00g $MgCl_2 \cdot 6H_2O$ and 0.65g $ZnCl_2$. The mixture obtained was stirred at room temperature for 2 hours, then dried at 120°C, and calcined at 650°C for 1 hour. The obtained molecular sieve was denoted as ZEP-14. XRF analysis showed that the contents of P_2O_5 , MgO and ZnO were 4.9%, 0.94% and 1.9% by weight respectively.

[0051] According to the method described in comparative example 1, the obtained ZEP-14 sample was aged under high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reaction evaluation are listed in table 2.

EXAMPLE 5:

[0052] 19g ZSM-5B molecular sieve sample (dry basis) was added into an aqueous solution prepared by mixing 1.62g 85%wt H_3PO_4 , 40g decationized water, 1.48g $MgCl_2 \cdot 6H_2O$ and 0.57g $Cu(NO_3)_2 \cdot 3H_2O$. The mixture was stirred at room temperature for 2 hours, then dried at 120°C, and calcined at 550°C for 2 hours. The obtained molecular sieve was denoted as ZEP-15. XRF analysis showed that this sample contained P_2O_5 4.9%wt, MgO 1.4%wt and CuO 0.91% wt.

[0053] According to the method described in comparative example 1, the ZEP-15 sample obtained was aged under high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reaction evaluation are listed in table 2.

EXAMPLE 6:

[0054] 19g ZSM-5C molecular sieve sample (dry basis) was added into an aqueous solution prepared by mixing 1.62g 85%wt H_3PO_4 , 40g decationized water, 0.53g $CaCl_2 \cdot 2H_2O$ and 1.15g $Cu(NO_3)_2 \cdot 3H_2O$. The obtained mixture was stirred at room temperature for 2 hours, then dried at 120°C, and calcined at 550°C for 2 hours. The molecular sieve obtained was denoted as ZEP-16. XRF analysis showed that the sample contained P_2O_5 4.9%, CaO 1.0% and CuO 1.9% by weight.

[0055] According to the method described in comparative example 1, the ZEP-16 sample obtained was aged under

high temperature hydrothermal condition. The results of XRD and nC_{14} pulse-micro-reaction evaluation are listed in table 2.

TABLE 2

Molecular sieves	Shape of XRD 24.4° peak	Conversion of nC_{14} %
D-2	Single peak	98.0
D-3	Single peak	95.5
ZEP-11	Single peak	99.6
ZEP-12	Single peak	98.6
ZEP-13	Single peak	99.3
ZEP-14	Single peak	97.5
ZEP-15	Single peak	92.2
ZEP-16	Single peak	90.5

It can be observed from table 2 that after introducing the transition metals such as Ni and Zn, the molecular sieves have maintained a single peak at $2\theta = 24.4^\circ$ in XRD pattern and high conversion of nC_{14} .

EXAMPLE 7

[0056] Based on a weight ratio of molecular sieve: alumina sol (calculated in Al_2O_3): kaolin of 15:15:70 by weight (dry basis), five catalysts were prepared by ordinary spray drying method using D-2, D-3, ZEP-11, ZEP-13, ZEP-15 molecular sieve samples without being aged as active components. A commercial catalyst CHP-1 (containing 20 wt% HZSM-5 molecular sieve produced by Zhoucun Catalyst Plant of Qilu Petrochemical Co.) for producing lower carbon olefins was selected as comparative catalyst. The above six catalysts were aged at $800^\circ C$ with 100% steam atmosphere for 4 hours, and evaluated by micro-reactor with light diesel fuel fraction as feedstock and fluidized fixed bed reactor with VGO as feedstock.

[0057] The results of micro-reaction evaluation with light diesel fuel fraction as feedstock are listed in table 3. The evaluation conditions were at a reaction temperature of $520^\circ C$, a catalyst/oil ratio of 3.2, a weight hourly space velocity of $16\ h^{-1}$ and a catalyst fed amount of 5.0g. The light oil had a boiling range of $229\sim 340^\circ C$.

[0058] The results of catalytic pyrolysis reaction on fluidized fixed bed reactor are listed in table 4. The evaluation conditions were as follows: reaction temperature at $700^\circ C$, catalyst to oil ratio 10, feeding hourly space velocity $10\ h^{-1}$, and water/oil weight ratio 80:20. The feedstock used was a VGO fraction having a boiling range of $346\sim 546^\circ C$.

[0059] From table 3 and table 4, it can be observed that the ethylene yield is remarkably increased by the introduction of transition metal of Ni, Zn, or Cu into the molecular sieves.

TABLE 3.

Molecular sieves	HZSM-5	D-2	D-3	ZEP-11	ZEP-13	ZEP-15
Conversion, wt%	44.0	62.38	61.01	63.92	64.05	63.21
Cracking gas yield, wt%	16.76	27.23	26.46	27.63	27.65	26.98
Ethylene	0.82	2.88	3.02	3.51	3.46	3.32
Propylene	6.50	7.57	7.32	7.34	7.61	7.92
Butenes	5.63	4.95	4.20	4.71	4.82	5.22

TABLE 4

Molecular sieve	HZSM-5	D-2	D-3	ZEP-11	ZEP-13	ZEP-15
Conversion, wt%	89.93	91.02	90.51	92.72	93.63	90.75
Product distribution, wt% Cracking gas yield, wt %	62.75	69.70	70.50	70.18	71.30	69.80
Ethylene	17.25	20.77	20.32	23.20	23.95	20.98
Propylene	18.91	22.47	19.57	21.66	22.08	21.33

TABLE 4 (continued)

Molecular sieve	HZSM-5	D-2	D-3	ZEP-11	ZEP-13	ZEP-15
Butenes	12.11	10.69	11.39	8.37	7.68	9.35
$C_2=C_3=C_4$	48.27	53.13	51.28	53.23	53.71	51.66
Gasoline($C_5 \sim 221^\circ\text{C}$)	24.81	15.22	13.16	14.33	14.96	14.21
LCO($221 \sim 330^\circ\text{C}$)	6.51	5.33	5.77	4.18	3.79	5.38
HCO($>330^\circ\text{C}$)	3.56	3.65	3.72	3.10	2.58	3.87
Coke	6.37	6.10	6.85	8.21	7.37	6.74

Claims

1. A pentasil-type molecular sieve containing composition which comprises from 85 to 98%wt pentasil-type zeolite which has a $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio from 15 to 60; from 1 to 10%wt phosphorus (based on P_2O_5); from 0.3 to 5%wt Mg or Ca (based on its oxide); and from 0.3 to 5%wt of a metal selected from Ni, Cu or Zn (based on its oxide).
2. The molecular sieve composition according to claim 1, comprising from 88 to 95%wt pentasil-type zeolite which has a $\text{SiO}_2/\text{Al}_2\text{O}_3$ molar ratio from 15 to 60; from 2 to 8%wt phosphorus (based on P_2O_5); from 0.5 to 3%wt Mg or Ca (based on its oxide); and from 0.5 to 3% of a metal selected from Ni, Cu or Zn (based on its oxide).
3. The molecular sieve composition according to claim 1 or claim 2, wherein said pentasil-type zeolite is a molecular sieve having a structure type of ZSM-5, ZSM-8, or ZSM-11.
4. The molecular sieve composition according to claim 3, wherein said pentasil-type zeolite is a molecular sieve having a structure type of ZSM-5.
5. The molecular sieve composition according to any preceding claim, wherein said pentasil-type zeolite has a SiO_2 to Al_2O_3 molar ratio from 15 to 40.
6. A method for preparing said composition according to claim 1, comprising :

a pentasil-type zeolite is firstly added to an aqueous solution which contains a phosphorus-containing compound, magnesium or calcium compound and a transition metal selected from Ni, Cu or Zn compound, homogeneously mixed and impregnated for above 0.5 hour, the obtained mixture contains (in dry basis) 85 to 98%wt pentasil-type molecular sieves, 1 to 10%wt phosphorus (based on P_2O_5), 0.3 to 5%wt magnesium or calcium (based on oxide), and 0.3 to 5%wt of a metal selected from Ni, Cu or Zn (based on oxide); the mixture is then dried, and calcined at 450 to 650°C for 1 to 4 hours.
7. A method according to claim 6 wherein the components of the mixture, and the amounts thereof, are defined in any of claims 2 to 5.
8. The method according to claim 6, wherein said phosphorus-containing compound is phosphoric acid, hydrogen phosphate or phosphate.
9. The method according to claim 6 or 8, where said phosphorus-containing compound is phosphoric acid.
10. The method according to claim 6 or 7, wherein said magnesium or calcium compound and/or said Ni, Cu or Zn compound is its nitrate or chloride.
11. The method according to claim 6, wherein the water to solid weight ratio of said mixture is (1 to 3): 1.
12. Use of a molecular sieve composition according to any of claims 1 to 5 in the catalytic cracking of hydrocarbons to produce ethylene and propylene.

Patentansprüche

1. Zusammensetzung, die Molekularsiebe vom Pentasil-Typ enthält, welche von 85 bis 98 Gew.% Zeolith des Pentasil-Typs mit einem molaren Verhältnis von $\text{SiO}_2/\text{Al}_2\text{O}_3$ von 15 bis 60, von 1 bis 10 Gew.% Phosphor (basierend auf P_2O_5), von 0,3 bis 5 Gew.% Mg oder Ca (basierend auf deren Oxiden) und von 0,3 bis 5 Gew.% eines Metalls ausgewählt aus Ni, Cu oder Zn (basierend auf deren Oxiden) umfasst.
2. Molekularsiebzusammensetzung nach Anspruch 1, die von 88 bis 95 Gew.% eines Zeoliths des Pentasil-Typs mit einem molaren Verhältnis von $\text{SiO}_2/\text{Al}_2\text{O}_3$ von 15 bis 60, von 2 bis 8 Gew.% Phosphor (basierend auf P_2O_5), von 0,5 bis 3 Gew.% Mg oder Ca (basierend auf deren Oxiden) und von 0,5 bis 3 Gew.% eines Metalls ausgewählt aus Ni, Cu oder Zn (basierend auf deren Oxiden) umfasst.
3. Molekularsiebzusammensetzung nach Anspruch 1 oder Anspruch 2, wobei das Zeolith des Pentasil-Typs ein Molekularsieb ist, das eine Struktur des Typs ZSM-5, ZSM-8 oder ZSM-11 aufweist.
4. Molekularsiebzusammensetzung nach Anspruch 3, wobei das Zeolith des Pentasil-Typs ein Molekularsieb ist, das eine Struktur des Typs ZSM-5 aufweist.
5. Molekularsiebzusammensetzung nach einem der vorstehenden Ansprüche, wobei das Zeolith des Pentasil-Typs ein molares Verhältnis zwischen SiO_2 und Al_2O_3 von 15 bis 40 aufweist.
6. Verfahren zur Herstellung der Zusammensetzung nach Anspruch 1, wobei zunächst ein Zeolith des Pentasil-Typs einer wässrigen Lösung zugegeben wird, die eine phosphorhaltige Verbindung, eine Magnesium- oder Calciumverbindung und eine Verbindung eines Übergangsmetalls ausgewählt aus Ni, Cu oder Zn enthält, homogen gemischt und für mehr als 0,5 Stunden imprägniert wird, wobei die erhaltene Mischung (bezogen auf Trockensubstanz) 85 bis 98 Gew.% Molekularsiebe des Pentasil-Typs, 1 bis 10 Gew.% Phosphor (basierend auf P_2O_5), 0,3 bis 5 Gew.% Mg oder Ca (basierend auf deren Oxiden) und 0,3 bis 5 Gew.% eines Metalls ausgewählt aus Ni, Cu oder Zn (basierend auf deren Oxiden) enthält, die Mischung anschließend getrocknet und bei 450 bis 650 °C 1 bis 4 Stunden lang calciniert wird.
7. Verfahren nach Anspruch 6, wobei die Bestandteile der Mischung und deren Mengen in den Ansprüchen 2 bis 5 definiert sind.
8. Verfahren nach Anspruch 6, wobei die phosphorhaltige Verbindung Phosphorsäure, Hydrogenphosphat oder Phosphat ist.
9. Verfahren nach Anspruch 6 oder 8, wobei die phosphorhaltige Verbindung Phosphorsäure ist.
10. Verfahren nach Anspruch 6 oder 7, wobei die Magnesium- oder Calciumverbindung und/oder die Ni-, Cu-, oder Zn-Verbindung als Nitrat oder Chlorid vorliegt.
11. Verfahren nach Anspruch 6, wobei das Gewichtsverhältnis Wasser zu Feststoff der Mischung (1 bis 3): 1 beträgt.
12. Verwendung einer Molekularsiebzusammensetzung nach Ansprüchen 1 bis 5 in der katalytischen Spaltung von Kohlenwasserstoffen zum Herstellen von Ethylen und Propylen.

Revendications

1. Composition contenant un tamis moléculaire du type pentasil qui comprend de 85 à 98 % en poids de zéolite du type pentasil, laquelle présente un rapport molaire $\text{SiO}_2/\text{Al}_2\text{O}_3$ de 15 à 60 ; de 1 à 10 % en poids de phosphore (sur la base de P_2O_5) ; de 0,3 à 5 % en poids de Mg ou de Ca (sur la base de son oxyde) ; et de 0,3 à 5 % en poids d'un métal choisi parmi Ni, Cu ou Zn (sur la base de son oxyde).
2. Composition de tamis moléculaire selon la revendication 1, comprenant de 88 à 95 % en poids de zéolite du type pentasil, laquelle présente un rapport molaire $\text{SiO}_2/\text{Al}_2\text{O}_3$ de 15 à 60 ; de 2 à 8 % en poids de phosphore (sur la base de P_2O_5) ; de 0,5 à 3 % en poids de Mg ou de Ca (sur la base de son oxyde) ; et de 0,5 à 3 % en poids d'un métal choisi parmi Ni, Cu ou Zn (sur la base de son oxyde).

EP 0 903 178 B1

3. Composition de tamis moléculaire selon la revendication 1 ou 2, dans laquelle ladite zéolite du type pentasil est un tamis moléculaire possédant une structure du type ZSM-5, ZSM-8 ou ZSM-11.
- 5 4. Composition de tamis moléculaire selon la revendication 3, dans laquelle ladite zéolite du type pentasil est un tamis moléculaire possédant une structure du type ZSM-5.
5. Composition de tamis moléculaire selon l'une quelconque des revendications précédentes, dans laquelle ladite zéolite du type pentasil présente un rapport molaire SiO_2 à Al_2O_3 de 15 à 40.
- 10 6. Procédé de préparation de ladite composition selon la revendication 1, comprenant les étapes consistant à : ajouter tout d'abord une zéolite du type pentasil à une solution aqueuse qui contient un composé contenant du phosphore, un composé de magnésium ou de calcium et un composé d'un métal de transition choisi parmi Ni, Cu ou Zn, effectuer un mélange homogène et une imprégnation pendant plus de 0,5 heure, le mélange obtenu contient (sur une base sèche) 85 à 98 % en poids de tamis moléculaires du type pentasil, 1 à 10 % en poids de phosphore (sur 15 la base de P_2O_5), 0,3 à 5 % de magnésium ou de calcium (sur la base de l'oxyde) et 0,3 à 5 % en poids d'un métal choisi parmi Ni, Cu ou Zn (sur la base de l'oxyde) ; le mélange est alors séché et calciné à une température de 450 à 650° C pendant 1 à 4 heures.
- 20 7. Procédé selon la revendication 6, dans lequel les composants du mélange et les quantités de ceux-ci sont définis selon l'une quelconque des revendications 2 à 5.
8. Procédé selon la revendication 6, dans lequel ledit composé contenant du phosphore est l'acide phosphorique, l'hydrogène phosphate ou le phosphate.
- 25 9. Procédé selon la revendication 6 ou 8, où ledit composé contenant du phosphore est l'acide phosphorique.
10. Procédé selon la revendication 6 ou 7, dans lequel ledit composé de magnésium ou de calcium et/ou ledit composé de Ni, Cu ou Zn est son nitrate ou son chlorure.
- 30 11. Procédé selon la revendication 6, dans lequel le rapport en poids eau/solides dudit mélange est (1 à 3):1.
12. Utilisation d'une composition de tamis moléculaire selon l'une quelconque des revendications 1 à 5 dans le craquage catalytique d'hydrocarbures pour produire de l'éthylène et du propylène.